

Bianco Carrara

TECHNICAL CHARACTERISTICS

ATTRIBUTES

Country Of Origin

Italy

Availability

Good

Block Size Dimensions

Medium/Large

Prevailing Applications

Interior/Exterior

Rate of Change Slab/Photo

Limited

Compressive Strength

1309 Kg/cm²

After Freezing

1114 Kg/cm²

Ultimate Tensile Strength

202 Kg/cm²

Coef. Thermal Expansion

0,0055mm/m⁰C

Water Absorption

0.18%

Impact Test/Min. Fall Height Frictional

56.00cm

Wear Test

1.12mm

Bulk Density

2550kg/m³